

## Technical specification of Kraft Liner (KL)

Physical properties	
GSM	200± 4
Burst strength (KPa)	470 – 530
RCT (KN/m)	3.321
Tensile (N)	189.80
Cobb 60	25-30
Moisture (%)	7.5±1

**Area temperature: (23±1)<sup>0</sup>C**

**Area moisture: (50±2) %**