

Technical specification of Semi Chemical Fluting (SCF)

Physical properties	
GSM	127 ± 3
CMT	300-320
RCT (KN/m)	1.8-2.0
Cobb 60	30-35
Moisture (%)	7.5±1

Area temperature: (23±1)⁰C

Area moisture: (50±2) %