

Technical specification of Test Liner Super type (TLS)

Physical properties	
GSM	127 ± 3
Burst strength (KPa)	300-320
RCT (KN/m)	0.9
Tensile (N)	104
Cobb 60	25-30
Moisture (%)	7.5±1

Modern Paper Co.